

KEMFLOR 617 SL

PU TOP COAT – SELF LEVELING

Rev.00-241110

PRODUCT DESCRIPTION	
<p>Kemflor 617 SL is two-pack, high performance, branched polyurethane SL Floor top coat, for use in heavy-duty applications. It is used as a part of a system comprising a primer, PU screed and PU SL in areas exposed to heavy chemical and atmospheric corrosion has gloss retention properties. When fully cured, it forms an extremely tough and abrasion resistant finish.</p>	
INTENDED USES	
<p>Power Plants, Refineries, Offshore structure, Petrochemicals, Pharma units.</p>	
SPECIFICATION DATA	
Thickness	1 mm
Type	2 pack
Shade	Range
Finish	Semi Glossy
Chemical Base	Polyester Polyol Cured with Aromatic Diisocyanate
Mixing Ratio	5:1/wt
Coverage kg/sq.m.	1.45
Recommended No. Of Coats	1
Re-coating Interval	Min. 12 hrs
Surface Dry Time	3 hrs
Curing Time	7 days
Pot Life	30 min.
Shelf Life (under std. condition)	6 months
Recommended System	634 must be top of 617
Pack Size	30 kg
<p>Note: These figures are theoretical under controlled conditions and may vary depending upon site conditions i.e. temp., humidity, surface porosity, surface profile, handling of material etc.</p>	
DIRECTION OF USE	
<p>SURFACE PREPARATION:</p> <p>As is the case with every coating scheme, the surface profile is of utmost importance. In order to achieve optimum bonding between substrate and coating, it is necessary to apply product only on fully dry and neatly cleaned surfaces.</p>	

KEMFLOR 617 SL

PU TOP COAT – SELF LEVELING

Rev.00-241110

Precautionary measures for new concrete floors:

Newly laid concrete surfaces are; For the first month or so after pouring, "green" meaning i.e. wet and alkaline. New concrete should be allowed to cure for 28 days prior to coating because of the concerns over the effect of water on floor coating adhesion. Check the moisture level (should be below 5%) prior to application.

Precautionary measures for old concrete floors:

Surface should be free from dust, grease, oil, laitance, loose material, old coatings etc. Generally cleaning with Kleenol or equivalent is enough to remove grease/oil. Smooth, aged concrete may be etched with dilute hydrochloric acid for suitable roughness and better adhesion of the epoxy flooring. In case of heavy oil & grease contamination, existing partial coating or structurally unsound concrete layer has occurred or old coatings are present mechanical cleaning is advisable.

KEMFLOR 617 APPLICATION:

After surface preparation, depending upon the system adopted KemFlor 617 can be applied on primer or other product. Stir well before mixing then add the KemFlor 617 parts, under continuous stirring by a very slow speed stirrer. DO NOT MIX BY HAND. Remove all material from each can. Scrape the sides of the container several times to ensure complete mixing. Be careful to not introduce any air bubbles while mixing. Apply by Roller / Brush and allow it to cure.

CLEAN UP

For cleaning of application equipment and tools use Chembond's thinner no.4.

MAINTENANCE

For maximum life expectancy, routinely sweep and wash floors with conventional detergent cleaners. Do not steam clean: all spills powder or liquid should be cleaned up immediately. Inspect the floor regularly for wear, breaks or damages, if found any immediately consult with Chembond's technical service personnel or authorized applicator.

SAFETY PRECAUTIONS

Take care to avoid skin or eye contact and breathing vapours. In the event of the skin contact immediately wash thoroughly. In the event of eye contact, wash continuously for 15 minutes in water and seek medical advice. Wear protective clothing, gloves, and safety glasses while using this product. If inhalation occurs, move to fresh air and seek medical advice in case of difficulty in breathing. Keep material away from heat, flames, and sources of ignition. For further details read Material Safety Data Sheet.

LIMITATIONS OF LIABILITY

This information is based on our current level of knowledge. It is given in a good faith but it is not intended to guarantee any particular properties. The users must satisfy themselves that there are no circumstances requiring additional information or precautions or the verification of details given herein.



Chembond Chemicals Limited

Chembond Centre
EL-71, MIDC Mahape,
Navi Mumbai 400 710
INDIA

Tel: (91 22) 66143000 / 315
Fax: (91 22) 768 1294
E-mail: sales@chembondcoatings.com
Website: www.chembondindia.com