

KEMFLOR 634

WATER BASED ALIPHATIC PU COATING

Rev.00-241110

PRODUCT DESCRIPTION	
<p>KemFlor 634 is a two-pack, high performance, Water Based Aliphatic PU coating a topcoat in heavy-duty applications. It can be used as a Finish Coat on an Epoxy Floor System or PU 1 mm SL. It is strongly recommended on PU SL KemFlor 617 1mm /2mm.</p>	
INTENDED USES	
<p>As Top coat for Floor coating in industries, pharma units & cold storages.</p> <ul style="list-style-type: none"> • Resists splash and spillage of dilute organic acids • Excellent resistance to splash and spillage of most alkalis • Excellent resistance to UV • Resists concentrated salt solutions • Withstands most of petroleum and aromatic solvents 	
SPECIFICATION DATA	
Thickness	50 micron
Type	2 pack
Shade	Clear
Finish	Matt
Chemical Base	WB Polyol Cured with Aliphatic Isocyanate
Mixing Ratio	4:1/wt
Coverage kg/sq.m.	0.12
Recommended No. Of Coats	2
Re-coating Interval	Min. 12 hrs
Surface Dry Time	3 hrs
Curing Time	7 days
Pot Life	30 min.
Shelf Life (under std. condition)	6 months
Recommended System	Various
Pack Size	25 kg
<p>Note: These figures are theoretical under controlled conditions and may vary depending upon site conditions i.e. temp., humidity, surface porosity, surface profile, handling of material etc.</p>	
DIRECTION OF USE	
<p>SURFACE PREPARATION: As is the case with every coating scheme, the surface profile is of utmost importance. In order to achieve optimum bonding between substrate and coating, it is necessary to apply product only on fully dry and neatly cleaned surfaces.</p>	



Chembond Chemicals Limited

Chembond Centre
EL-71, MIDC Mahape,
Navi Mumbai 400 710
INDIA

Tel: (91 22) 66143000 / 315
Fax: (91 22) 768 1294
E-mail: sales@chembondcoatings.com
Website: www.chembondindia.com

KEMFLOR 634

WATER BASED ALIPHATIC PU COATING

Rev.00-241110

Precautionary measures for new concrete floors:

Newly laid concrete surfaces are; For the first month or so after pouring, "green" meaning i.e. wet and alkaline. New concrete should be allowed to cure for 28 days prior to coating because of the concerns over the effect of water on floor coating adhesion. Check the moisture level (should be below 5%) prior to application.

Precautionary measures for old concrete floors:

Surface should be free from dust, grease, oil, laitance, loose material, old coatings etc. Generally cleaning with Kleenol or equivalent is enough to remove grease/oil. Smooth, aged concrete may be etched with dilute hydrochloric acid for suitable roughness and better adhesion of the epoxy flooring. In case of heavy oil & grease contamination, existing partial coating or structurally unsound concrete layer has occurred or old coatings are present mechanical cleaning is advisable.

KEMFLOR 634 APPLICATION:

Ensure that the surface to be top coated is smooth, zero level and free of any surface impurities. Stir the components thoroughly and then mix parts in given mixing ratio to complete uniformity, additional water may be added, but not recommended during application. Use of roller/ spray.

Notes:

- Do not apply when temperature falls below 10°C or when relative humidity rises above 75% or during rain, fog or mist.
- Brushes or spray equipment should be cleaned with water other wise equipment is liable to be damaged.
- Mix quantity, which can be used off within the utilization period.

CLEAN UP

For cleaning of application equipment and tools use water.

MAINTENANCE

For maximum life expectancy, routinely sweep and wash floors with conventional detergent cleaners. Do not steam clean: all spills powder or liquid should be cleaned up immediately. Inspect the floor regularly for wear, breaks or damages, if found any immediately consult with Chembond's technical service personnel or authorized applicator.

SAFETY PRECAUTIONS

Take care to avoid skin or eye contact and breathing vapours. In the event of the skin contact immediately wash thoroughly. In the event of eye contact, wash continuously for 15 minutes in water and seek medical advice. Wear protective clothing, gloves, and safety glasses while using this product. If inhalation occurs, move to fresh air and seek medical advice in case of difficulty in breathing. Keep material away from heat, flames, and sources of ignition. For further details read Material Safety Data Sheet.

LIMITATIONS OF LIABILITY

This information is based on our current level of knowledge. It is given in a good faith but it is not intended to guarantee any particular properties. The users must satisfy themselves that there are no circumstances requiring additional information or precautions or the verification of details given herein.



Chembond Chemicals Limited

Chembond Centre
EL-71, MIDC Mahape,
Navi Mumbai 400 710
INDIA

Tel: (91 22) 66143000 / 315
Fax: (91 22) 768 1294
E-mail: sales@chembondcoatings.com
Website: www.chembondindia.com